

DURAL **iTe**[®] **D100**

CEMENT-BASED
MICRO SKIM COAT

DATA SHEETS

VERSION 1.00

Contents

1.	TECHNICAL DATA	2
2.	MATERIAL SAFETY DATA	4
4.	THEORETICAL (VOC) CONTENT	9
5.	SHORT REPORT VOC	10
6.	VOC CONFIRMATION NOTICE	11
9.	SUGGESTED SPECIFICATIONS	12





DURALiTe[®]D100

CEMENT-BASED
MICRO SKIM COAT

1. TECHNICAL DATA

1.1 DESCRIPTION

DURALiTe[®]D100 white cement-based ultra fine finishing skim plaster is a durable external and internal finishing compound for walls. **DURALiTe[®]D100** is designed to be applied over new or existing sand cement plasters

- scratched, smooth or rough wall finishes, or partition joints and ceilings, or painted surfaces, to create a silky-smooth appearance. **DURALiTe[®]D100** will not swell or soften when it gets wet, as it is cement based. **DURALiTe[®]D100** can be sandpapered.

1.2 SURFACE PREPARATION

NOTE: For both external as well as internal application. The surface must be hard, sound, dry and free of dust, dirt and other materials such as old gypsum plasters, grease, oil or any other contaminant.

1.2.1 DURALiTe[®]D100 OVER PREVIOUSLY PAINTED SURFACES:

All previously painted surfaces must be cleaned properly by means of high-pressure washer (externally) or scraper and brush/wire brush on internal surfaces. Remove all loose/flaky paint off the wall. Once cleaned apply **DURALiTe[®]D100** straight over in the manner set out under section 1.4 APPLICATION.

Where enamel and epoxy paints are used prime with iTe SLURRY Keying Promoter prior to application of **DURALiTe[®]D100**.

1.2.2 DURALiTe[®]D100 OVER NEW OR EXISTING SAND CEMENT PLASTERED WALLS:

The plaster must be fully cured before applying **DURALiTe[®]D100**. Scrape/Brush off any loose debris off the wall. Slightly wet the wall to prevent instant water absorption out of the **DURALiTe[®]D100**.

1.2.3 DURALiTe[®]D100 OVER CONCRETE SURFACES:

It is of the utmost importance to remove all releasing oils or grease from the concrete before applying **DURALiTe[®]D100**, by degreasing the surfaces with degreasing soap and rinsing afterwards with water. Once this is done prime the surface with iTe SLURRY Keying Promoter.

1.2.4 DURALiTe[®]D100 OVER GYPSUM - OR FIBRE CEMENT BOARD:

Use joining tape or fine wire mesh over butt joints. Apply **DURALiTe[®]D100** over the joint allowing it to semi set up. Once this has occurred apply a 1 - 3mm **DURALiTe[®]D100** layer over the entire surface to achieve a smooth and even finish.

1.3 MIXING

Use approx. 14.0 litres of water per 40 kg or approx. 4 litres per 15 kg bag. Do NOT over-water. Add the powder to the required amount of clean cool water in a clean mixing container whilst using an electric paddle mixer until a lump free plaster is produced. This will take approximately 3 minutes. Stop the mixer and scrape the inside of the mixing vessel to allow any unmixed product to fall onto the paste. Allow product to slake for 5 minutes. Briefly remix the **DURALiTe[®]D100** and then plaster onto the desired surface.

Mixed **DURALiTe[®]D100** should be applied within 30 minutes at 20°C after mixed. This time is extended at lower temperatures and reduced at higher temperatures.



DURALiTe[®]D100

**CEMENT-BASED
MICRO SKIM COAT**

1.4 APPLICATION

DURALiTe[®]D100 can be applied over existing paint, sand cement plaster, concrete, fibre cement as well as gypsum boards. The following application method is used once preparation is complete. (see 1.2 Surface Preparation for different surfaces):

Apply **DURALiTe[®]D100** with a trowel in an even and smooth manner, covering the entire surface area. Allow **DURALiTe[®]D100** set up – test by touching the surface, if no indent shows and no product is set on your hand it is ready to be floated. Wetting the surface slightly with a plaster brush, use a rubber float to flatten area and bring fine material to the surface. Strike off excess fines with a steel float and smooth off the surface. Allow surface to harden then polish with a steel float.

Flash off/set up time can take longer/shorter depending on weather conditions. It is also affected by the porosity of the surface onto which **DURALiTe[®]D100** is applied.

1.5 THICKNESS

Recommended thickness ranges from 1mm to 3mm thickness.

1.6 COVERAGE

Approximately 1 kg of **DURALiTe[®]D100** per 1mm thickness per m². E.g. one 40kg bag of **DURALiTe[®]D100** will give enough material to cover approximately 40m² at an average thickness of 1mm.

NOTE: The coverage figure is based on a relatively flat surface. Additional material should be allowed for where the surface is rough or uneven.

1.7 GENERAL

All data given was tested at a room temperature of 20°C and 50% humidity. Please be aware that the technical data may alter if the climatic conditions are in contrast to that in which the product has been tested, either hardening more quickly or setting slower.

1.8 WARRANTY

DURALiTe[®]D100 is guaranteed to be free of any manufacturing defect. iTe Products further warrants that if **DURALiTe[®]D100** is applied in accordance with the relevant method statement issued for the specific project, by an approved applicator, the system is guaranteed for the life of the application.

1.9 WARNING

Do not ingest. Keep away from children and pets. Do not empty into a drain. Wear rubber gloves, and in the event of contamination, rinse thoroughly with cold water. Seek medical advice if irritation or discomfort persists. For further information, consult the relevant health and safety data sheet.

1.10 GREEN BUILDING COUNCIL VOC REQUIREMENTS

DURALiTe[®]D100 contains no Volatile Organic Compounds and therefore is totally compliant with all relevant requirements to be classed as “green.” The standard short report, theoretical VOC content declaration

and VOC confirmation notice is available on request or can be downloaded from our website - www.iteproducts.co.za.

1.11 IMPORTANT NOTICE

The information supplied in our literature or given by our employees is given in good faith. We reserve the right to update this information at any time without prior notice.



DURAL **iTe**[®] **D100**

CEMENT-BASED
MICRO SKIM COAT

2. MATERIAL SAFETY DATA

2.1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND COMPANY

Name of substance/preparation:

Commercial product name: **DURALiTe[®]D100**

2.1.1 USE OF SUBSTANCE / PREPARATION

Residential/Industrial/Commercial.

Use for: Skimming/plastering wall surfaces. Available in 10Kg and 35Kg Paper Bags

All other areas of application to be agreed with the Application Engineering/Technical Marketing Department of the manufacturer.

2.1.2 COMPANY NAME

Manufacturer/distributor: iTe Products (Pty) Ltd Street: 7 Clarke Street South

State/postal code/city: Alrode, 1451

Telephone: +27 11 864 4918

Telefax: +27 11 864 2123

Information about the Safety Data Sheet: +27 11 864 4918

eMail: info@iteproducts.co.za

2.2 HAZARDS IDENTIFICATION

2.2.1 CLASSIFICATION

Classification (67/548/EEC, 1999/45/EC):

R-Phrase Description – irritant to eyes

This product is not a dangerous preparation within the meaning of Directive 1999/45/EC.

2.2.2 LABELLING

Labelling (67/548/EEC, 1999/45/EC):

R-Phrase Description – 36/38 Irritant to eyes

S-Phrase Description

2.2.3 FURTHER HAZARD TO HUMAN AND ENVIRONMENT:

The product does not have any further hazards

2.3 COMPOSITION/INFORMATION ON INGREDIENTS

2.3.1 CHEMICAL CHARACTERIZATION:

Mixture

2.3.2 DESCRIPTION:

Mixture of cement and sand mixture with other nonhazardous additions



DURAL **D100**

**CEMENT-BASED
MICRO SKIM COAT**

2.4 FIRST-AID MEASURES

2.4.1 GENERAL INFORMATION:

Under ordinary workplace conditions: No special measures required.

2.4.2 AFTER CONTACT WITH THE SKIN

Wash with plenty of water or water and soap.

2.4.3 AFTER CONTACT WITH THE EYES

Rinse immediately with plenty of water. Seek medical advice in case of continuous irritation.

2.4.4 AFTER SWALLOWING

If conscious, give several small portions of water to drink. Do not induce vomiting. In cases of sickness seek medical advice (show label if possible).

2.4.5 ADVICE FOR THE PHYSICIAN

Due to its physical properties, may cause mechanical irritation. Product may agglutinate in the gastro-intestinal tract. Medical assistance should be sought. Depending on the symptoms, invasive measures may be necessary.

2.5 FIRE-FIGHTING MEASURES

2.5.1 SUITABLE EXTINGUISHING MEDIA

Water spray, water mist, extinguishing powder, foam, carbon dioxide.

2.5.2 EXTINGUISHING MEDIA WHICH MUST NOT BE USED FOR SAFETY REASONS

Water jet.

2.5.3 SPECIAL EXPOSURE HAZARDS ARISING FROM THE SUBSTANCE OR PREPARATION ITSELF, COMBUSTION PRODUCTS, RESULTING GASES

No further relevant information available

2.5.4 SPECIAL PROTECTIVE EQUIPMENT FOR FIRE FIGHTING

No further relevant information available

2.6 ACCIDENTAL RELEASE MEASURES

2.6.1 PERSONAL PRECAUTIONS

Wear a dust mask

2.6.2 ENVIRONMENTAL PRECAUTIONS

Do not allow to enter into sewer, drainage or potable water systems

2.6.3 METHODS FOR CLEANING UP

Take up mechanically and dispose of according to local/state/federal regulations.

2.6.4 FURTHER INFORMATION:

Observe notes under section 7 with regards to safe handling. Observe section 8 for information on personal protective equipment.



DURAL **iTe**[®] **D100**

**CEMENT-BASED
MICRO SKIM COAT**

2.7 HANDLING AND STORAGE

2.7.1 HANDLING

Precautions for safe handling:

Avoid dust formation.

Precautions against fire and explosion:

No special measures required

2.7.2 STORAGE

Conditions for storage rooms and vessels:

No special measures required

Advice for storage of incompatible materials:

not applicable .

2.8 EXPOSURE CONTROLS AND PERSONAL PROTECTION EQUIPMENT

2.8.1 EXPOSURE LIMITS

2.8.2 EXPOSURE LIMITED AND CONTROLLED

2.8.3 EXPOSURE IN THE WORK PLACE LIMITED AND CONTROLLED

General protection and hygiene measures:

Do not breathe dust. Do not eat when handling.

Personal protection equipment Respiratory protection

In case of dust formation: fine dust mask without protection rating .

Eye protection

Recommendation in case of dust formation: tight fitting protective goggles .

2.8.4 EXPOSURE TO THE ENVIRONMENT LIMITED AND CONTROLLED

Prevent material from entering surface waters and soil.

2.9 PHYSICAL AND CHEMICAL PROPERTIES

2.9.1 GENERAL INFORMATION

Physical state / form.

solid - powder

Colour

off white

Odour

odourless

2.9.2 IMPORTANT INFORMATION ABOUT THE PROTECTION OF HEALTH, SAFETY AND THE ENVIRONMENT

Property: Value: Method:

Melting point / melting range

not applicable

Boiling point / boiling range

not applicable

Flash point.

not applicable

Auto-ignition temperature.

product is not self-igniting

Lower explosion limit (LEL)

not applicable

Vapour pressure.

not applicable

Bulk density

900 kg/m³ (DIN EN ISO 60)

Water solubility / miscibility

Insoluble sets in water

pH-Value

11

Viscosity (dynamic)

not applicable



DURAL **iTe**[®] **D100**

**CEMENT-BASED
MICRO SKIM COAT**

2.10 STABILITY AND REACTIVITY

2.10.1 GENERAL INFORMATION:

If stored and handled in accordance with standard industrial practices no hazardous reactions are known.

2.10.2 CONDITIONSTO AVOID

none known .

2.10.3 MATERIALSTO AVOID

none known .

2.10.4 HAZARDOUS DECOMPOSITION PRODUCTS

If stored and handled properly: none known . At increased temperature: acetic acid .

2.11 TOXICOLOGICAL INFORMATION

2.11.1 GENERAL INFORMATION:

According to our present state of knowledge no damaging effect expected when treated in accordance with standard industrial practices and local regulations where applicable.

2.11.2 TOXICOLOGICALTESTS

Acute toxicity Primary irritation:

Eyes: irritating effect

Sensitization:

no sensitizing effects known

Further information:

The product shows the following aspects:

Irritant

2.12 ECOLOGICAL INFORMATION

2.12.1 ECOTOXICITY

No expected damaging effects to aquatic organisms.

Effects in sewage treatment plants (bacteria toxicity: respiration-/reproduction inhibition):

According to current knowledge adverse effects on water purification plants are not expected.

2.12.2 MOBILITY

No further relevant information available

2.12.3 BIO-ACCUMULATION POTENTIAL

No adverse effects expected.

2.12.4 OTHER HARMFUL EFFECTS

2.12.5 ADDITIONAL INFORMATION

General information:



DURAL **iTe**[®] **D100**

**CEMENT-BASED
MICRO SKIM COAT**

2.13 DISPOSAL CONSIDERATIONS

2.13.1 MATERIAL

Do not allow product to reach sewerage system

Disposal should be in accordance with local, state or national legislation.

Mix product residue with water, allow to harden and dispose of as construction waste

2.13.2 UNCLEANNED PACKAGING

Recommendation:

Completely discharge packaging. Paper packaging may be recycled

2.14 TRANSPORT INFORMATION

2.14.1 LANDTRANSPORT ADR AND RID

Road ADR:

Valuation

Not regulated for transport

Railway RID:

Valuation

Not regulated for transport

2.14.2 TRANSPORT BY SEA IMDG-CODE

Valuation

Not regulated for transport Marine Pollutant

no

2.14.3 AIRTRANSPORT ICAO-TI/IATA-DGR

Valuation

Not regulated for transport

2.15 REGULATORY INFORMATION

2.15.1 NATIONAL REGULATIONS

National and local regulations must be observed.

For information on labelling please refer to section 2 of this document.

2.16 OTHER INFORMATION

2.16.1 MATERIAL

The above information describes exclusively the safety requirements of the product(s) and is based on our present-day knowledge. It does not represent a guarantee for the properties of the product(s) described in terms of the legal warranty regulations. Properties of the product are to be found in the respective product leaflet.

2.17 FURTHER INFORMATION:

Commas appearing in numerical data denote a decimal point. Vertical lines in the left-hand margin indicate changes compared with the previous version. This version supersedes all previous versions.



DURAL **iTe**[®] **D100**

CEMENT-BASED
MICRO SKIM COAT

3. THEORETICAL(VOC)CONTENT

3.1 PRODUCT:

DURALiTe[®] D100 Plaster Skimming Compound

3.2 ABBREVIATIONS

S.G. = Specific Gravity

g/ml = grams/millilitre

g/l = grams/litre

3.3 FORMULAS

Sum of VOC's in Sealer/Primer formulation = VOC %

$VOC (g/l) = VOC \% \times S.G. \times 10$

3.4 S.G. (g/ml) = 1.00g/ml

3.5 VOC % = 0%

3.6 $VOC (g/l) = 0 \times 1.00 \times 10 = 0g/l$

Maximum VOC content (Specified by Green Building Council of South Africa): 50g/l

Peter Funke

Product Development Manager

DURAL **iTe**[®] **D100**

CEMENT-BASED
MICRO SKIM COAT

4. SHORT REPORT VOC

24 October 2022

Short Report: Product DURALiTe D100 Plaster Skimming Compound

iTe Products **DURALiTe[®] D100** Plaster Skimming Compound meets the Green Building Council of South Africa's credit criteria for the following reasons:

Maximum VOC allowable (gms/litre) 50g/l
DURALiTe[®] D100 0g/l

*This is based on the fact that the product contains no organic solvents.
I declare the above information to be correct*

Signed:



Shaun Van Heerden



DURAL **iTe**[®] **D100**

CEMENT-BASED
MICRO SKIM COAT

5. VOC CONFIRMATION NOTICE

24 October 2022

To: All interested Parties

Dear Sir/Madam,

Re: GBCSA requirements for VOC levels in flooring adhesives, sealers and primers

We hereby confirm that **DURALiTe**[®] Plaster Skimming Compound as manufactured by iTe Products (Pty) Ltd comply with the GBCSA requirements in respect of permissible VOC levels in flooring adhesives, sealers and primers.

The attached Short Report, VOC Datasheet and this signed letter provides the necessary supporting documentation required as per page 107 of the GBCSA Technical Manual.

The Applicator or Contractor must provide written confirmation that **DURALiTe**[®] **D100** is to be used in the application.

Should there be any questions or queries, please contact the writer at 082 772 9137 or via e-mail at sales@iteproducts.co.za.

Yours faithfully,



Shaun Van Heerden



DURAL **iTe**[®] **D100**

CEMENT-BASED
MICRO SKIM COAT

6. SUGGESTED SPECIFICATION

Apply _____m² **DURALiTe[®] D100** Plaster Skimming Compound in accordance with the manufacturer's specifications to a thickness of _____mm after surface preparation is complete.