

LEVEL *iTe* WX[®]

**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

MATERIAL SAFETY DATA SHEET

Contents

1. TECHNICAL DATA	2
2. MATERIAL SAFETY DATA	4
3. THEORETICAL(VOC)CONTENT	9
4. SHORT REPORT VOC	10
5. OC CONFIRMATION NOTICE	11
6. WARRANTY	12
7. INFORMATION SHEET	13
8. SUGGESTED SPECIFICATION	16





LEVELiTe[®]WX

**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

1. TECHNICAL DATA

1.1 DESCRIPTION

LEVELiTe[®]WX Fibre Reinforced self-levelling screed and smoothing compound developed for over wood type applications that sets to 20MPa. It is a free flowing screeding compound that has been specifically formulated for smoothing over wooden and other surfaces prior to the installation of floor coverings.

LEVELiTe[®]WX is suitable for use on sound solid well bound wooden surfaces, cementitious screeds, power-floated concrete surfaces, hardened, well adhered old non-watersoluble adhesive residues that have been ground to remove excess residue, and soundly adhered ceramic and similar surfaces. The applied compound can be walked on after 3 to 4 hours. Floor coverings – such as carpeting, vinyl tiles and sheeting, laminated wood – can typically be installed 24 hours after application.

LEVELiTe[®]WX can be applied in thicknesses from 0,3mm to 10mm in a single application.

Usage rate is 1,4Kg per m²per 1mm thickness.

Once cured **LEVELiTe[®]WX** is resistant to moisture and will not swell or soften when exposed to moisture.

1.2 SURFACE PREPARATION

NOTE: For internal use only due to the inability to control environmental factors such as wind or heat. It is recommended that direct to ground sub-floors be protected from rising damp to prevent dimensional changes in the floor covering (confirm the maximum permissible moisture content that the floor covering or adhesive can tolerate). **LEVELiTe[®]WX** is resistant to rising moisture and should not swell or delaminate if exposed to reasonable moisture. Standard European practice has evolved that when vinyl flooring is to be installed, the substrate is to be sealed with a water based epoxy moisture barrier such as **VAPORiTe[®] +PLUS**, or similar. The surface must be hard, sound, dry and free of dust, dirt and other materials such as grease, oil and paint, waxes and oils.

Plywood and similar boarded surfaces should be securely fitted onto a well-bonded structurally sound substructures, where flexing is kept to a minimum

1.3 PRIMING

BONDiTe[®] primer and bonding agent is an essential component in the priming prior to application of **LEVELiTe[®]WX** over raw uncoated wood and Cementitious surfaces. It acts as a pore sealer which will maintain the flow life and prevent air bubbles rising through the applied **LEVELiTe[®]WX** screed smoothing compound. Accordingly it is necessary to prime all surfaces with **BONDiTe[®]**. With very smooth non-absorbent sub-floors e.g. Sealed wooden floors, epoxy coated water barriers, and ceramic tiles it is essential to apply **iTe SLURRY[®]** to promote better Inter-coat adhesion and/or to lightly grind the surface to promote adhesion. Waxes and oils should be sanded down prior to applying and priming agent

1.4 MIXING

Use 5 Litres of water per 20 kg bag. Do **NOT** over-water. Add the powder to the required amount of clean cool water in a clean mixing container whilst using a +/-600 rpm electric paddle mixed until a lump free screed is produced. This will take approximately 3 to 4 minutes. Stop the mixer and scrape the inside of the mixing vessel to allow any unmixed product to fall onto the paste. Briefly remix the **LEVELiTe[®]WX** and then discharge onto the affected floor.

Mixed **LEVELiTe[®]WX** should be applied within 5 minutes at 20°C. This time is extended at lower temperatures and reduced at higher temperatures.



LEVELiTe[®]WX

FIBRE REINFORCED SELF-LEVELLING SCREED for over wood applications

1.5 APPLICATION

Pour the mixed **LEVELiTe[®]WX** onto the prepared sub-floor. The mixed mortar will flow out and self-level. Use a suitable notched epoxy rake or spreader to obtain the required thickness; while a long-handled pin leveller/rake with height adjustment will simplify this operation and yield more consistent results. A long handled spiked roller must be used to prevent air blisters from marring the finished surface. **LEVELiTe[®]WX** has excellent self-healing properties which extend for some 30 minutes or longer after the pour, which minimises cold joints and surface irregularities.

1.6 THICKNESS

LEVELiTe[®]WX can be applied at a minimum thickness of 0.3mm to a maximum of 10mm in a single application.

Multiple layers can be applied to the dry previous layer with a **BONDiTe[®]** application on top of the previous application, in order to build up to the required thickness. Contact our technical advisors for detailed information. Bulking-up of the product can be a viable option for significant sub-floor deviations where speed of drying is a factor.

1.7 COVERAGE

Approximately 1.4 kg of **LEVELiTe[®]WX** per 1 mm thickness per m². E.g. one 20kg bag of **LEVELiTe[®]WX** will give enough material to cover approximately 4.7m² at an average thickness of 3mm.

NOTE: The coverage figure is based on a flat level surface. Additional material should be allowed for where the surface is rough or uneven.

1.8 GENERAL

All data given was tested at a room temperature of 20°C and 50% humidity. Please be aware that the technical data may alter if the climatic conditions are in contrast to that in which the product has been tested, either hardening more quickly or setting slower.

1.9 WARRANTY

LEVELiTe[®]F10 is guaranteed to be free of any manufacturing defect.

1.10 WARNING

Do not ingest. Keep away from children and pets. Do not empty into a drain. Wear rubber gloves, and in the event of contamination, rinse thoroughly with cold water. Seek medical advice if irritation or discomfort persists. For further information, consult the relevant health and safety data sheet.

1.11 GREEN BUILDING COUNCIL VOC REQUIREMENTS

LEVELiTe[®]WX contains no Volatile Organic Compounds and therefore is totally compliant with all relevant requirements to be classed as "green." The standard short report, theoretical VOC content declaration and VOC confirmation notice is available on request or can be downloaded from our website - www.iteproducts.co.za.

1.12 IMPORTANT NOTICE

The information supplied in our literature or given by our employees is given in good faith. We reserve the right to update this information at any time without prior notice.

LEVELiTe[®]WX
**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

2. MATERIAL SAFETY DATA

2.1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND COMPANY

Name of substance/preparation:

Commercial product name:.....**LEVELiTe[®]WX**

2.1.1 USE OF SUBSTANCE / PREPARATION

Commercial/Residential.

Used for: Levelling of floors

All other areas of application to be agreed with the Application Engineering/Technical Marketing Department of the manufacturer.

2.1.2 COMPANY NAME

Manufacturer/distributor:.....iTe Products (Pty) Ltd

Street:.....7 Clarke Street South

State/postal code/city:.....Alrode, 1451

Telephone:.....+27 11 864 4918

Telefax:.....+27 11 864 2123

Information about the Safety Data Sheet:.....+27 11 864 4918

eMail:.....info@iteproducts.co.za

2.2 HAZARDS IDENTIFICATION

2.2.1 CLASSIFICATION

Classification (67/548/EEC, 1999/45/EC):

R-Phrase Description – irritant to eyes

This product is not a dangerous preparation within the meaning of Directive 1999/45/EC.

2.2.2 LABELLING

Labelling (67/548/EEC, 1999/45/EC):

R-Phrase Description – 36/38 Irritant to eyes S-Phrase Description

2.2.3 FURTHER HAZARDS TO HUMAN AND ENVIRONMENT:

The product does not have any further hazards

2.3 COMPOSITION/INFORMATION ON INGREDIENTS

2.3.1 CHEMICAL CHARACTERIZATION:

Mixture

2.3.2 DESCRIPTION:

Mixture of cement and sand mixture with other non hazardous additions

2.4 FIRST-AID MEASURES

2.4.1 GENERAL INFORMATION:

Under ordinary workplace conditions: No special measures required.



LEVEL **iTe**[®] **WX**

FIBRE REINFORCED SELF-LEVELLING SCREED for over wood applications

2.4.2 AFTER CONTACT WITH THE SKIN

Wash with plenty of water or water and soap. First-aid measures cont.

2.4.3 AFTER CONTACT WITH THE EYES

Rinse immediately with plenty of water. Seek medical advice in case of continuous irritation.

2.4.4 AFTER SWALLOWING

If conscious, give several small portions of water to drink. Do not induce vomiting. In cases of sickness seek medical advice (show label if possible).

2.4.5 ADVICE FOR THE PHYSICIAN

Due to its physical properties, may cause mechanical irritation. Product may agglutinate in the gastrointestinal tract. Medical assistance should be sought. Depending on the symptoms, invasive measures may be necessary.

2.5 FIRE-FIGHTING MEASURES

2.5.1 SUITABLE EXTINGUISHING MEDIA

Water spray, water mist, extinguishing powder, foam, carbon dioxide.

2.5.2 EXTINGUISHING MEDIA WHICH MUST NOT BE USED FOR SAFETY REASONS

Water jet .

2.5.3 SPECIAL EXPOSURE HAZARDS ARISING FROM THE SUBSTANCE OR PREPARATION ITSELF, COMBUSTION PRODUCTS, RESULTING GASES

No further relevant information available

2.5.4 SPECIAL PROTECTIVE EQUIPMENT FOR FIRE FIGHTING

No further relevant information available

2.6 ACCIDENTAL RELEASE MEASURES

2.6.1 PERSONAL PRECAUTIONS

Wear a dust mask

2.6.2 ENVIRONMENTAL PRECAUTIONS

Do not allow to enter into sewer, drainage or potable water systems

2.6.3 METHODS FOR CLEANING UP

Take up mechanically and dispose of according to local/state/federal regulations.

2.6.4 FURTHER INFORMATION:

Observe notes under section 7 with regards to safe handling

Observe section 8 for information on personal protective equipment.

2.7 HANDLING AND STORAGE

2.7.1 HANDLING

Precautions for safe handling:

Avoid dust formation.

Precautions against fire and explosion: No special measures required

LEVEL iTe[®] WX
**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

2.7.2 STORAGE

Conditions for storage rooms and vessels:

- No special measures required

Advice for storage of incompatible materials:

- not applicable .

2.8 EXPOSURE CONTROLS AND PERSONAL PROTECTION EQUIPMENT

2.8.1 EXPOSURE LIMITS

2.8.2 EXPOSURE LIMITED AND CONTROLLED

2.8.2.1 EXPOSURE IN THE WORK PLACE LIMITED AND CONTROLLED

General protection and hygiene measures:

Do not breathe dust. Do not eat when handling.

Personal protection equipment

Respiratory protection

In case of dust formation: fi ne dust mask without protection rating .

Eye protection

Recommendation in case of dust formation: tight fi tting protective goggles .

2.8.2.2 EXPOSURE TO THE ENVIRONMENT LIMITED AND CONTROLLED

Prevent material from entering surface waters and soil.

2.9 PHYSICAL AND CHEMICAL PROPERTIES

2.9.1 GENERAL INFORMATION

Physical state / form:..... solid - powder

Colour:..... grey - brown

Odour:..... odourless

2.9.2 IMPORTANT INFORMATION ABOUT THE PROTECTION OF HEALTH, SAFETY AND THE ENVIRONMENT

Property: Value: Method:

Melting point / melting range :..... not applicable

Boiling point / boiling range :.....not applicable

Flash point:..... not applicable

Auto-ignition temperature: product is not self-igniting

Lower explosion limit (LEL) :..... not applicable

Vapour pressure:..... not applicable

Bulk density:.. 1300-1500 kg/m³ (DIN EN ISO 60)

Water solubility/miscibility:..... Insoluble sets in water

pH-Value :..... 11

Viscosity (dynamic) :..... not applicable



LEVEL **iTe**[®] **WX**

FIBRE REINFORCED SELF-LEVELLING SCREED for over wood applications

2.10 STABILITY AND REACTIVITY

2.10.1 GENERAL INFORMATION:

If stored and handled in accordance with standard industrial practices no hazardous reactions are known.

2.10.2 CONDITIONS TO AVOID NONE KNOWN.

2.10.3 MATERIALS TO AVOID NONE KNOWN.

2.10.4 HAZARDOUS DECOMPOSITION PRODUCTS

If stored and handled properly: none known. At increased temperature: acetic acid .

2.11 TOXICOLOGICAL INFORMATION

2.11.1 GENERAL INFORMATION:

According to our present state of knowledge no damaging effect expected when treated in accordance with standard industrial practices and local regulations where applicable.

2.11.2 TOXICOLOGICAL TESTS

Acute toxicity Primary irritation: Eyes: irritating effect Sensitization: no sensitizing effects known Further information:

The product shows the following aspects:

Irritant

2.12 ECOLOGICAL INFORMATION

2.12.1 ECOTOXICITY

No expected damaging effects to aquatic organisms.

Effects in sewage treatment plants (bacteria toxicity: respiration-/reproduction inhibition):

According to current knowledge adverse effects on water purification plants are not expected.

2.12.2 MOBILITY

No further relevant information available

2.12.3 BIO-ACCUMULATION POTENTIAL

No adverse effects expected.

2.12.4 OTHER HARMFUL EFFECTS

2.12.5 ADDITIONAL INFORMATION

General information:

2.13 DISPOSAL CONSIDERATIONS

2.13.1 MATERIAL

Do not allow product to reach sewerage system

Disposal should be in accordance with local, state or national legislation.

Mix product residue with water, allow to harden and dispose of as construction waste.

2.13.2 UNCLEANNED PACKAGING

Recommendation: Completely discharge packaging. Paper packaging may be recycled.



LEVEL **iTe**[®] **WX**

FIBRE REINFORCED SELF-LEVELLING SCREED for over wood applications

2.14 TRANSPORT INFORMATION

2.14.1 LAND TRANSPORT ADR AND RID ROAD ADR:

Valuation :..... Not regulated for transport Railway RID:

Valuation :..... Not regulated for transport

2.14.2 TRANSPORT BY SEA IMDG-CODE

Valuation :..... Not regulated for transport

Marine Pollutant :..... no

2.14.3 AIR TRANSPORT ICAO-TI/IATA-DGR

Valuation :..... Not regulated for transport

2.15 REGULATORY INFORMATION

2.15.1 NATIONAL REGULATIONS

National and local regulations must be observed.

For information on labelling please refer to section 2 of this document.

2.16 OTHER INFORMATION

2.16.1 MATERIAL

The above information describes exclusively the safety requirements of the product(s) and is based on our present-day knowledge. It does not represent a guarantee for the properties of the product(s) described in terms of the legal warranty regulations. Properties of the product are to be found in the respective product leaflet.

2.17 FURTHER INFORMATION:

Commas appearing in numerical data denote a decimal point. Vertical lines in the left-hand margin indicate changes compared with the previous version. This version supersedes all previous versions.



LEVELiTe[®]WX

**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

3. THEORETICAL(VOC)CONTENT

3.1 PRODUCT:

LEVELiTe[®]WX Self Levelling Floor Screed Compound

3.2 ABBREVIATIONS

S.G. = Specific Gravity g/ml = grams/millilitre g/l = grams/litre

3.3 FORMULAS

Sum of VOC's in Sealer/Primer formulation = VOC % VOC (g/l) = VOC % x S.G. x 10

4.4 S.G. (G/ML) = 1.00G/ML 4.5 VOC % = 0% 4.6 VOC (G/L) = 0 X 1.00 X 10 = 0G/L

Maximum VOC content (Specified by Green Building Council of South Africa): 50g/l



Peter Funke

Director



LEVELiTe[®]WX

**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

4. SHORT REPORT VOC

1 July 2025

Short Report: Product LEVELiTe F10 Self Levelling Floor Screed

*iTe Products **LEVELiTe[®]WX** Self Levelling Floor Screed Compound meets the Green Building Council of South Africa's credit criteria for the following reasons:*

Maximum VOC allowable (gms/litre) 50g/l

LEVELiTe[®]WX 0g/l

This is based on the fact that the product contains no organic solvents. I declare the above information to be correct Signed:



*Peter Funke
Director*



LEVELiTe[®]WX

**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

5. OC CONFIRMATION NOTICE

1 July 2025

To: All interested Parties

Dear Sir/Madam,

Re: GBCSA requirements for VOC levels in flooring adhesives, sealers and primers

We hereby confirm that **LEVELiTe F10, F30, F50 and F100** Self Levelling Floor Screed Compounds as manufactured by **iTe Products** (Pty) Ltd comply with the GBCSA requirements in respect of permissible VOC levels in flooring adhesives, sealers and primers.

The attached Short Report, VOC Datasheet and this signed letter provides the necessary supporting documentation required as per page 107 of the GBCSA Technical Manual.

The Flooring Contractor must provide written confirmation that **LEVELiTe F10, F30 or F50** is to be used in the installation of the floor covering.

Should there be any questions or queries, please contact the **iTeTeam** at **sales@iteproducts.co.za**.

Yours faithfully,



Peter Funke

Director



LEVELiTe[®]WX

**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

6. WARRANTY

iTe PRODUCTS warrants that **LEVELiTe[®]WX** is manufactured to comply with international EN standards for P2 and P3 class self levelled screeds in respect of Flow determination, setting time, Drying Kinetics, and compressive strength.

LEVELiTe[®]WX is compliant with EN expansion and shrinkage standards, is resistant to substrate moisture levels below 5% screed moisture, and will not expand or delaminate. It will also not powder or soften.

LEVELiTe[®]WX self-levels to an end finish compliant with SANS 10070:2007, provided the thickness of application allows the elimination of deviations. The surface hardens to 18MPa, and is suitable for light castor traffic and conventional foot traffic. **LEVELiTe[®]WX** is typically recommended for use in residential and light commercial applications, provided the sub-base allows.

This warranty is based on the substrate being sound, dry and free of contamination. All application is to be carried out in strict compliance with the method statement as issued.

iTe Products further warrants that the products are manufactured to strict quality control standards and that the products supplied are free of defect. We cannot be held responsible for failure due to the substrate failing, or physical or excessive mechanical damage occurring to the applied product. It must be noted that the product is porous and that it will stain if exposed to oil or chemical spillages.



LEVELiTe[®]WX

FIBRE REINFORCED SELF-LEVELLING SCREED for over wood applications

7. INFORMATION SHEET

F10, F30 and F50 Self Levelling Compound Information Sheet.

As a basis for evaluation of self-levelling compounds we use the applicable European Standard EN 13813:2002. This information sheet tries to set out the criteria used in the evaluation, and where our **LEVELiTe[®]** products are positioned. Products are classified under performance classes, P2, P3, P3R, P4 and P4R. The table at the end of this sheet sets these out.

DESCRIPTION:	RANGE OF CONFORMITY – WHAT IS/ARE GOOD VALUES.	EXPLANATION
1. Compressive strength	Wide range of conformities are applicable but most screeding compounds range between 20-30MPa	What does MPa really mean? The actual load or force the material can handle before deforming (crushing in this case) Calc: 1 MPa = 1N/mm ² = 0.102 kg force/mm ² E.g. The maximum load for a trolley wheel that has a contact area of 10mmx25mm on a screed with a compressive strength of 20MPa would be: 20 MPa = N (force)/250mm ² (area) N(force) = 5000 Newton Therefore, the point load for a surface contact area of the 10mmx25mm wheel can be as much as +/-510kg load per wheel For the same wheel size and a 30 MPa substrate the wheel could exert a load of 765kg
2. Flexural strength	Wide range of flexural strength are applicable but good values would range between 6-10 MPa	Flexural strength is the tensile force that the material can withstand. A typical example of this is the higher the flexural strength the better the product can withstand excessive shrinkage without cracking or slab deflections due to loading of the slabs.
3. Wear resistance	The best values attainable for abrasion resistance is in the class AR0.5 in accordance with the BCA testing method	This is one of the most important features in high traffic areas such as hospital corridors and the like in conjunction with vinyl application. The class rating AR0.5 means that the average wear resistance is no more than 50µm over the given test area.
4. Bonding strength	Bonding strength is the amount of force needed to pull the screed from actual substrate. This is described in MPa or N/mm ² . A very good class would be a B2.0 = 2MPa	The bond strength is a very important aspect to prevent delamination of the screed. Screeds are always subject to some or other force within itself. Reason for this can be internal or external. Internal forces are created by shrinkage or expansion of the screed itself and external factors would be issues such as deflection of suspended slabs when placed under load.
5. Setting time	A good setting time is around 30-40 min on Self Levelling Screeds.	Fast track construction in today's world calls for quick setting systems. A fine line is also drawn here to allow the contractor enough time to apply the product but have it cure sufficiently to be able to lay the floor covering 24h later
6. Consistency /Flow	These are more based on internal testing of the manufacturer and flow should be consistent over the duration up until initial setting of the screeding compound	Proper flow of the screeding compound facilitates the system to find its true level and to fill all deviations and voids in the substrate leaving a smooth and level surface to apply the floor coverings on to.
7. Shrinkage in dry environment	Shrinkage is not allowed to be in excess of 1mm/m. A safe shrinkage number would be between 0.3-0.5mm/m	Shrinkage comes from excess water in the system evaporating into the air. This leaves voids in the screed resulting in shrinkage. If the shrinkage becomes excessive (>1mm/m) then internal forces will exceed the internal flexural strength on the screed, resulting in cracking.
8. Expansion in a wet environment	Expansion is not allowed to be in excess of 1mm/m. A safe expansion number would be 0.3-0.5mm/m	Most levelling compounds are subject to expansion under wet/moist conditions. An excess expansion will result in the internal forces exceeding the screeding bond strength. Bonding strength should therefore be around 2MPa to avoid any delamination.



LEVELiTe[®]WX

FIBRE REINFORCED SELF-LEVELLING SCREED for over wood applications

DESCRIPTION:	RANGE OF CONFORMITY – WHAT IS/ARE GOOD VALUES.	EXPLANATION
1. Compressive strength	Wide range of conformities dependent on application requirements—15 to 40MPa+	MPa equates to the actual load or force the material can handle before deforming (being crushed). Calc: 1MPa = 1N/mm ² = 0.102kg force/mm ² Eg. A trolley wheel with a contact surface area of 25 x 10mm, on a 25MPa LEVELiTe F30 screed can bear a maximum load of 6375kg
2. Flexural strength	Wide range of conformities dependent on application requirements— 6 to 10MPa	Flexural strength is the tensile force that the material can withstand. I.e. The higher the flexural strength, the better the product can withstand excessive shrinkage without cracking, or slab deflections due to loading of the slabs.
3. Wear resistance	The best values attainable for abrasion resistance is in the class AR0.5 in accordance with the BCA test method	This is one of the most important features in high traffic areas such as hospital corridors and the like in conjunction with vinyl application. The class rating AR0.5 means that the average wear is no more than 50µm over the test area.
4. Bonding strength	Bonding strength is the amount of force needed to pull the screed from the substrate. This measured in MPa or N/mm ² . A very good class would be a B2.0 = 2MPa	The bond strength is critical to prevent delamination of the screed. Screeds are continually subject to forces within itself, either internal or external. Internal shrinkage or expansion, or external factors such as deflection of slabs can cause delamination.
5. Setting time	Initial Set—25 to 30 minutes Walkability—2 h30min Final Set—24 Hours 75% Final hardness—72 hours Final Hardness—28 Days	Due to site conditions, the newly laid screed must be able to take foot traffic asap. This should be in approximately 2 hours. If the setting is too rapid, the product is very difficult to apply without dry joints. The drying of the screed should enable installation of vinyl after 24 hours. (thickness dependent)
6. Consistency /Flow	The better the flow, the better the self-levelling properties. The flow should be consistent during the duration of the application until the initial set commences. The flow test should exceed 135mm diameter.	Proper flow of the screeding compound facilitates the system to find its true level and to fill all deviations and voids in the substrate, leaving a smooth and level surface ready for the application of floor coverings.
7. Shrinkage in dry environment	Shrinkage is not allowed to exceed 1mm/m1 (SANS 10070:2012). A safe shrinkage number would be between 0.3 and 0.5mm/m1	Shrinkage comes from excess water in the system evaporating into the air. This leaves voids in the screed resulting in shrinkage. If the shrinkage is excessive, (>1mm/m1), then the internal forces will exceed the internal flexural strength on the screed, resulting in cracking.
8. Expansion in a wet environment	Expansion is not allowed to exceed 1mm/m1 (SANS 10070:2012). A safe expansion number would be between 0.3 and 0.5mm/m1	Most levelling compounds are subject to expansion under wet/moist substrate conditions. An excess expansion will result in the internal forces exceeding the screed bond strength. Bonding strength should be around 2MPa to avoid any delamination.

CLASS:	FACTORS	PRODUCT
P2	Premises where there are no intense constraints. Static constraints, <2MPa, no castors, typically light commercial and residential.	LEVELiTe F10, F30, WX, FX
P3	Premises such as offices using castor chairs, corridors (eg hospitals) with trollies moved by hand, hospital wards and heavier trafficked commercial areas.	LEVELiTe F30, WX, FX
P3R	Premises classified as P3, which bear heavy rolling traffic (fork-lifts, heavy vehicles) or intense loads.	LEVELiTe F30, FX, F50
P4	Premises classified as P3, which bear heavy rolling traffic loads, intense loads or repetitive and severe shocks	LEVELiTe F50

LEVELiTe[®]WX
**FIBRE REINFORCED
 SELF-LEVELLING SCREED**
for over wood applications

						LEVELITE				
CLASS OF PERFORMANCE		P2	P3	P3R	P4R	F10	F30	F50	FX	FW
Flow Determination	Initial	Diameter 150mm				155mm	155mm	155mm		
	10 Min	-	-	-	-	155mm	155mm	155mm		
	20 Min	135mm	135mm			155mm	155mm	155mm		
Initial Set		No Specification - Ideally should be >20 Minutes								
Walkable		No Specification - Ideally should be <3 Hours								
Layable		No Specification - Ideally should be <48 Hours								
Drying Kinetics				<2.5%	<2.5%	<1%	<1%	<1%		
Abrasion resistance			<8 a 10			TBA	<2	<2		
Flexural Strength 28 days						>6	>10	>12		
MPa										
Compressive Strength 28 days MPa		>10	>18			18	25	35		
Adhesion Strength	Initial	>0.5	>1			>1.0	>1.5	>1.5		
	Wet	>0.4	>0.8			>0.4	>0.8	>1.2		



LEVELiTe[®]WX

**FIBRE REINFORCED
SELF-LEVELLING SCREED**
for over wood applications

8. SUGGESTED SPECIFICATION

Apply _____m² **LEVELiTe[®]WX** self-levelling compound system in accordance with the manufacturer's specifications to a thickness of _____mm after priming with the required primer primer.